SPECIFICATION

FOR

600V ETHYLENE PROPYLENE RUBBER INSULATED
POLYCHLOROPRENE SHEATHED FLEXIBLE CABLE
Code: 600V MM-CAR-2PNCT-SB

Quantity		***************************************	
Your Ref. No.			
Our Ref. No.			
Signed by	TWO	ghal.	
	Takanob	u Watanabe	
	Man	ager	

Engineering Dept. I
Electric Wire & Cable Business Unit

Proterial, Ltd.

REV. No.	Issue date	Item	Prepared by	Reviewed by	Approved b y
<u>-</u>	Feb. 21, 2024	FIRST ISSUE	X Jumane K. Yamane		Tuku T. Watanabe
	····				
					!
				:	:

1. Scope

This specification covers 600V Ethylene Propylene Rubber Insulated Polychloroprene Sheathed Flexible Cable, which is reference to Japanese Electrical Appliance and Material Safety Law or Japanese Electrical Facility Regulation, and Manufacture's Standard.

This cable shall have flame retardant property as per IEEE Std. 383-1974 paragraph 2.5, Vertical Tray Flame Test (VTFT).

2. Construction and Materials

2. 1 Conductor

Conductor shall be stranded flexible conductor consisting of tinned annealed copper wires.

A suitable separator tape shall be applied over the conductor.

2. 2 Insulation

Insulation shall consist of black flame retardant ethylene propylene rubber compound. A suitable tape shall be applied over the insulation. Nominal thickness shall be shown in the table 1.

Ave. thick. : not less than 90% of the nominal thickness Min. thick. : not less than 80% of the nominal thickness

2. 3 Braided shield

Braided shield shall consist of tinned annealed copper wires and staple fiber. A suitable tape shall be applied over the shield braid.

2. 4 Sheath

Sheath shall consist of black flame retardant polychloroprene compound. Nominal thickness shall be shown in the table 1.

Ave. thick. : not less than 90% of the nominal thickness Min. thick. : not less than 85% of the nominal thickness

A straight line shall be marked on the surface of the sheath.

2.5 Dimension

The dimension of the cable shall be in accordance with the table 1.

3. Marking

Manufacture's name and year of manufacture shall be marked by suitable methods.


4. <u>Inspection</u>

Inspection shall be made on the following items prior to shipment.

Properties	Standard to comply with	Requirements	Test interval	
Construction and dimensions	JIS C 3005 4.3	To comply with clause 2 and the attached table 1		
Withstand voltage test	JIS C 3005 4.6	To withstand AC 3000V for 1 min. 600V MM-CAR-2PNCT 1×95mm ² To withstand AC 3000V for 1 min. 600V MM-CAR-2PNCT 1×150mm ² 600V MM-CAR-2PNCT 1×185mm ²	Every shipment	
Conductor resistance	JIS C 3005 4.4	Not more than the value in the attached table 2	First shipment	
Insulation resistance	JIS C 3005 4.7	Not less than the value in the attached table 2		

5. Guide to use

This cable is designed for carrier drum system(cable tender system) as shown below.



Code : 600V MM-CAR-2PNCT-SB $1 \times 95 \text{mm}^2$, $1 \times 150 \text{mm}^2$, $1 \times 185 \text{mm}^2$)

Item		Unit	Specified Value			
No. of conductor		_	1	1	1	
	Nominal cross-section area	mm ²	95	150	185	
Conductor	Construction	No./mm	19/25/0.5	27/34/0. 45	37/25/0.5	
	Approx. diameter	mn	14. 4	18. 7	20. 2	
Nominal thickness of insulation		mm	2. 0	2. 0	2. 5	
Approx. thickness of braided shield		mn	0. 65	0. 65	0. 65	
Nominal thickness of sheath		mm	2. 7	2. 9	3. 2	
Approx. diameter of completed cable		mm	27	31	35	
Maximum di	ameter of completed cable	mm	28. 4	32. 6	36. 8	
Approx. we	ight of completed cable	kg/km	1370	1910	2490	

Table 2: Characteristic

Item	Unit	Specified Value		
Conductor nominal cross-section area	_	95	150	185
Maximum conductor resistance at 20℃	Ω/km	0. 210	0. 136	0. 108
Minimum insulation resistance at 20℃	MΩ·km	300	200	200
Permissible minimum bending radius	mm	170	190	210




Fig. 1 Cable cross section